

Technical data sheet for **PROTEGA WOOD-S**

PRODUCT DESCRIPTION

PROTEGA WOOD-S is a white, halogen free, waterborne intumescent paint.

SPECIAL PROPERTIES

PROTEGA WOOD-S is an intumescent paint that foams into a thick layer when exposed to high temperatures derived from flames or intensive heat radiation from fire. The porous layer of foam effectively extinguishes the flow of heat to the treated surface. PROTEGA WOOD-S should be sealed with approved topcoat, when used in areas with constant air humidity higher than 75% or when a washable surface is required.

FIELD OF APPLICATION

PROTEGA WOOD-S is used to prevent spread of fire in internal wall and ceiling linings made of solid wood or chip-board. PROTEGA WOOD-S is offered in flat white, but can on request be delivered in light pastel tone. Fully coloured PROTEGA WOOD-S can be supplied from factory when ordering minimum 500 kg. For further information, please consult design description for current system.

APPLICATION

The surface that is to be painted with PROTEGA WOOD-S must be untreated and free from dust and grease. Certain kinds of fatty wood, e.g. teak, should undergo a test coating of a small area to determine the adhesion. Application should be avoided at temperatures below +10°C. The paint should be kept at room temperature to aid easy application. The moisture in the wood must be carefully examined and it must not exceed 10% for undressed wood. Roller, brush or airless spraying can be used for application. Consult Protega AB or retailer for recommended type of tools. PROTEGA WOOD-S should be well stirred before application. Tools can be cleaned in water.

DRYING TIME

At a temperature of min. +23°C and an air humidity of max. 50%, following is applicable:

- 4 hours for each layer of coating.
- Dry to be sealed with approved topcoat after 12h.

PACKING

Plastic bucket containing 5kg and 12.5 kg 44 pc/pallet



PROTECTIVE MEASURES

Preventive measures: Avoid contact with skin and eyes.

Personnel safety devices: At handling where prolonged or repeated direct contact cannot be excluded protective gloves should be worn. Protective glasses are recommended when there is a risk of splashes. To avoid other types of direct contact suitable protective clothes are recommended. See further Safety Data Sheet.

ADDITIONAL DATA

Viscosity: High viscosity

Flash point: Non-combustible

Specific gravity: 1.3

Non.vol.contnt: 70%

Thickness: 300 g/m² wet paint will give 230 µm wet thickness and 160 µm dry thickness.

Thinner: Water

Storage: 12 months for unopened packing.

MUST BE PROTECTED AGAINST FROST

Surface B-s1,d0

wet paint quantity (g/m ²)	wet film (µm)	dry film (µm)
300	230	160

APPROVALS

According to different national standards e.g.

SBI EN 13823 (B-s1,d0),

Consult Protega or

retailer for additional information.

All information in this sheet is to be considered as guidelines collected from technical tests and practical knowledge of the product. This information may not be used as a basis or verification for other tests or systems. Protega AB is not responsible for other application fields or incorrect handling. The user must ensure that the last revision of this document is used. Please check on www.protega.se